

SB-190 EVERSEAL

DESCRIPTION: Versatile, high strength, hard setting, one-part sealant-adhesive. Superb tensile strength with excellent impact resistance. Water and weather proof.

USES:

Industries

- Automotive
- Construction
- Roofing
- Correctional facilities
- Manufacturing
- Safety surfaces
- Marine

Substrates

- Plastic
- PVC
- Fiberglass
- Metal
- Vinyl
- Glass
- Painted materials
- Cement
- Brick
- Wood

FEATURES:

- High strength
- Flexible
- Durable bond to material
- Allows for movement of dissimilar
- Does not become brittle or crack Excellent memory

materials

BENEFITS:

- Hard setting
- One part
- Easy application

Pick-proof

- Weather resistant
- Long service life
- Fast skinning
- Minimizes dirt and dust pickup
- Paintable
- Easy to match substrate

Not recommended for use with copper or soft expansion joints, polystyrene or styrene containing plastic.

APPLICATION: Interface and surfaces must be clean, dry and free of dust, dirt, oil and water proofing and release agents. Cut cartridge nozzle at slant to 1/4" hole and puncture inner seal, apply bead size as desired. Apply uniform bead with steady pressure. Tool immediately after application to ensure full contact with both sides of the joint area. Sealant starts to skin over in 20-25 minutes. Minimum application temperature of 50° F. Full cure is recommended prior to painting.

CLEANING: While uncured, remove excess material from tools with naptha or mineral spirits. See cautions on cleaner

SHELF LIFE: 12 months.

STORAGE: Unopened containers should be stored in a cool,

dry area. Keep above 40° F before use.

CAUTION: For industrial use only. Skin and eye irritant. Harmful if swallowed. Avoid contact with or breathing in of vapor and use adequate ventilation. Material on skin should be wiped and washed off with soap and water. For eyes, flush with water and seek medical attention.

SEE MATERIAL SAFETY DATA SHEET

PACKAGING: 10.3 oz. cartridge, 50 gallon drum.

COLOR: Translucent.

SPECIFICATIONS:

VOC Cure Time Tack-free Time Tensile Strength Tear Strength Elongation Staining Hardness, Shore A Viscosity

370 g/l 28 Days 18-24 Hours 2000 PSI Over 300 PLI 500% fully cured None 70-80 43.000 CPS

40% by weight Using 1/8" Bead ASTM-C679 Test Method ASTM-D412 Test Method ASTM D-624 Test Method ASTM-D412 Test Method TT-S-00230C Test Method TT-S-00230C Test Method

All values are typical at 75° F, 50% R.H. unless otherwise noted. Federal Specifications TT-S-00230C used when applicable.